

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
5 June 2003 (05.06.2003)

PCT

(10) International Publication Number
WO 03/046023 A1

- (51) International Patent Classification⁷: C08F 10/06, 4/02 (74) Agent: COLUCCI, Giuseppe; Basell Poliolefine Italia S.p.A., Intellectual Property, P.le G. Donegani, 12, I-44100 Ferrara (IT).
- (21) International Application Number: PCT/EP02/13471
- (22) International Filing Date: 26 November 2002 (26.11.2002) (81) Designated States (*national*): JP, US.
- (25) Filing Language: English (84) Designated States (*regional*): European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, SK, TR).
- (26) Publication Language: English
- (30) Priority Data: 01204694.2 27 November 2001 (27.11.2001) EP
Declarations under Rule 4.17:
— as to the applicant's entitlement to claim the priority of the earlier application (Rule 4.17(iii)) for all designations
— of inventorship (Rule 4.17(iv)) for US only
- (71) Applicant (*for all designated States except US*): BASELL POLIOLEFINE ITALIA S.P.A. [IT/IT]; Via Pergolesi, 25, I-20124 Milano (IT).
- (72) Inventors; and
(75) Inventors/Applicants (*for US only*): FERRARO, Angelo [IT/IT]; Via S. Stefano, 34, I-40125 Bologna (IT). BARUZZI, Giovanni [IT/IT]; Via Mario Azzi, 37, I-44100 Ferrara (IT). STEWART, Constantine, A. [US/US]; 2904 Santa Cruz Avenue SE, Albuquerque, NM 87106 (US).
- Published:
— with international search report
— before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: POROUS POLYMERS OF PROPYLENE

(57) Abstract: A porous polymer of propylene optionally containing up to 15% by weight of an alpha-olefins of formula $\text{CH}_2=\text{CHR}$ wherein R is a hydrogen atom or a $\text{C}_2\text{-C}_{10}$ alkyl radical having the following characteristics: a) in the Temperature Rising Elution Temperature analysis (TREF) a fraction eluted at a temperature range from 25°C to 97° higher than 20% of the total polymer eluted; and b) a pore volume (determined by mercury absorption) greater than 0.45 cc/g.



WO 03/046023 A1

POROUS POLYMERS OF PROPYLENE

The present invention relates to porous propylene polymers having enhanced properties, especially when used as support for catalyst systems for the polymerization of olefins. Catalyst components for the polymerization of olefins comprising a titanium compound supported on a magnesium halide in active form can be obtained in spherical particle form suitable for the manufacture of polymers with optimum morphological characteristics. Components of this type are described in US 3,953,414 and US 4,399,054. Specifically, the polymers obtained with the catalysts of US 4,399,054 are in spherical particle form having high flowability and bulk density values. The porosity (about 10% expressed in percentage of voids) and the surface area, however, are not sufficiently high for some industrial use. US 5,236,962 relates to crystalline propylene polymers having high porosity. When used as support for a catalyst system for the polymerization of the olefins the activities of the resulting catalyst are not quite satisfactory. Therefore it is desirable to find new porous polymers that, when used as support, can improve the activity of the resulting catalyst systems. Thus, according to a first object, the present invention provides a porous polymer of propylene, optionally containing up to 15% by weight of an α -olefin of formula $\text{CH}_2=\text{CHR}$ wherein R is a hydrogen atom or a $\text{C}_2\text{-C}_{10}$ alkyl radical, said porous propylene polymer having the following characteristics:

- a) in the Temperature Rising Elution Temperature analysis (TREF) a fraction eluted at a temperature range of from 25°C to 97° higher than 20% preferably higher than 30%; more preferably higher than 40% of the total polymer eluted; and
- b) a pore volume (determined by mercury absorption) greater than 0.45 cc/g; preferably greater than 0.50 cc/g; more preferably greater than 0.55 cc/g.

In a particular embodiment the porous propylene polymer object of the present invention is further characterized by a flexural modulus (METHOD ASTM D-5023) lower than 1200 Mpa, preferably lower than 1000 Mpa, more preferably lower than 900 Mpa.

In another particular embodiment the porous polymer of the present invention has a melting enthalpy lower than 90 J/g; preferably lower than 80 J/g; more preferably lower than 70 J/g.

In a suitable embodiment the polymer of the present invention is an homopolymer of propylene.


The polymer of the present invention has a high content of the so-called stereoblocks, i.e. of polymer fractions which, although predominantly isotactic, contain a not negligible amount of non-isotactic sequences of propylene units. In the conventional fractionation

techniques such as the TREF (Temperature Rising Elution Temperature) those fractions are eluted at temperatures lower than those necessary for the more isotactic fractions. Due to the particular morphology, the propylene polymers of the present invention are particularly suitable as inert support for catalyst component used in the polymerization of olefins.

Examples of catalyst components that can be supported on the propylene polymer object of the present invention are the metallocene compounds such as those described in WO 98/22486, WO 99/58539 WO 99/24446, USP 5,556,928, WO 96/22995, EP-485822, EP-485820, USP 5,324,800, EP-A-0 129 368 EP-A-0 416 815, EP-A-0 420 436, EP-A-0 671 404, EP-A-0 643 066 and WO-A-91/04257. Thus a further object of the present invention is a heterogeneous catalyst system comprising:

- A) a porous polymer of propylene according to the present invention;
- B) a metallocene compound; and
- C) an alumoxane or a compound able to form an alkylmetallocene cation.

Examples of metallocene compounds that can be used in the heterogeneous catalyst system of the present invention belongs to the following formula (I)




wherein $(\text{ZR}^1_m)_n$ is a divalent group bridging Cp and A; Z being C, Si, Ge, N or P, and the R^1 groups, equal to or different from each other, being hydrogen or linear or branched, saturated or unsaturated $\text{C}_1\text{-C}_{20}$ alkyl, $\text{C}_3\text{-C}_{20}$ cycloalkyl, $\text{C}_6\text{-C}_{20}$ aryl, $\text{C}_7\text{-C}_{20}$ alkylaryl or $\text{C}_7\text{-C}_{20}$ arylalkyl groups or two R^1 can form a aliphatic or aromatic $\text{C}_4\text{-C}_7$ ring;

Cp is a substituted or unsubstituted cyclopentadienyl group, optionally condensed to one or more substituted or unsubstituted, saturated, unsaturated or aromatic rings, containing from 4 to 6 carbon atoms, optionally containing one or more heteroatoms;

A is O, S, NR^2 , PR^2 wherein R^2 is hydrogen, a linear or branched, saturated or unsaturated $\text{C}_1\text{-C}_{20}$ alkyl, $\text{C}_3\text{-C}_{20}$ cycloalkyl, $\text{C}_6\text{-C}_{20}$ aryl, $\text{C}_7\text{-C}_{20}$ alkylaryl or $\text{C}_7\text{-C}_{20}$ arylalkyl, or A has the same meaning of Cp; M is a transition metal belonging to group 4, 5 or to the lanthanide or actinide groups of the Periodic Table of the Elements (IUPAC version);


the substituents X, equal to or different from each other, are monoanionic sigma ligands selected from the group consisting of hydrogen, halogen, R^3 , OR^3 , OCOR^3 , SR^3 , NR^3_2 and PR^3_2 , wherein R^3 is a linear or branched, saturated or unsaturated $\text{C}_1\text{-C}_{20}$ alkyl, $\text{C}_3\text{-C}_{20}$ cycloalkyl, $\text{C}_6\text{-C}_{20}$ aryl, $\text{C}_7\text{-C}_{20}$ alkylaryl or $\text{C}_7\text{-C}_{20}$ arylalkyl group, optionally containing one or more Si or Ge atoms; preferably, the substituents X are the same; m is 1 or 2, and

more specifically it is 1 when Z is N or P, and it is 2 when Z is C, Si or Ge; n is an integer ranging from 0 to 4; r is 0, 1 or 2; preferably 0 or 1; n is 0 when r is 0 or 2; p is an integer equal to the oxidation state of the metal M minus r+1; it ranges from 1 to 4;
The alumoxanes used in the catalyst according to the invention are considered to be linear, branched or cyclic compounds containing at least one group of the type:




wherein the substituents R^{17} , same or different, are described above.

In particular, alumoxanes of the formula:



can be used in the case of linear compounds, wherein n^1 is 0 or an integer from 1 to 40 and the substituents R^{17} are defined as above, or alumoxanes of the formula:



can be used in the case of cyclic compounds, wherein n^1 is an integer from 2 to 40 and the R^{17} substituents are defined as above. Examples of alumoxanes suitable for use according to the present invention are methylalumoxane (MAO), tetra-(isobutyl)alumoxane (TIBAO), tetra-(2,4,4-trimethyl-pentyl)alumoxane (TIOAO), tetra-(2,3-dimethylbutyl)alumoxane (TDMBAO) and tetra-(2,3,3-trimethylbutyl)alumoxane (TTMBAO). Particularly interesting cocatalysts are those described in WO 99/21899 and in WO01/21674 in which the alkyl and aryl groups have specific branched patterns. Non-limiting examples of aluminium compounds according to WO 99/21899 and WO01/21674 are:

tris(2,3,3-trimethyl-butyl)aluminium, tris(2,3-dimethyl-hexyl)aluminium,
tris(2,3-dimethyl-butyl)aluminium, tris(2,3-dimethyl-pentyl)aluminium, tris(2,3-dimethyl-heptyl)aluminium, tris(2-methyl-3-ethyl-pentyl)aluminium, tris(2-methyl-3-ethyl-hexyl)aluminium, tris(2-methyl-3-ethyl-heptyl)aluminium, tris(2-methyl-3-propyl-hexyl)aluminium, tris(2-ethyl-3-methyl-butyl)aluminium, tris(2-ethyl-3-methyl-pentyl)aluminium, tris(2,3-diethyl-pentyl)aluminium, tris(2-propyl-3-methyl-

butyl)aluminium, tris(2-isopropyl-3-methyl-butyl)aluminium, tris(2-isobutyl-3-methyl-pentyl)aluminium, tris(2,3,3-trimethyl-pentyl)aluminium, tris(2,3,3-trimethyl-hexyl)aluminium, tris(2-ethyl-3,3-dimethyl-butyl)aluminium, tris(2-ethyl-3,3-dimethyl-pentyl)aluminium, tris(2-isopropyl-3,3-dimethyl-butyl)aluminium, tris(2-trimethylsilyl-propyl)aluminium, tris(2-methyl-3-phenyl-butyl)aluminium, tris(2-ethyl-3-phenyl-butyl)aluminium, tris(2,3-dimethyl-3-phenyl-butyl)aluminium, tris(2-phenyl-propyl)aluminium, tris[2-(4-fluoro-phenyl)-propyl]aluminium, tris[2-(4-chloro-phenyl)-propyl]aluminium, tris[2-(3-isopropyl-phenyl)-propyl]aluminium, tris(2-phenyl-butyl)aluminium, tris(3-methyl-2-phenyl-butyl)aluminium, tris(2-phenyl-pentyl)aluminium, tris[2-(pentafluorophenyl)-propyl]aluminium, tris[2,2-diphenyl-ethyl]aluminium and tris[2-phenyl-2-methyl-propyl]aluminium, as well as the corresponding compounds wherein one of the hydrocarbyl groups is replaced with a hydrogen atom, and those wherein one or two of the hydrocarbyl groups are replaced with an isobutyl group.

Amongst the above aluminium compounds, trimethylaluminium (TMA), triisobutylaluminium (TIBAL), tris(2,4,4-trimethyl-pentyl)aluminium (TIOA), tris(2,3-dimethylbutyl)aluminium (TDMBA) and tris(2,3,3-trimethylbutyl)aluminium (TTMBA) are preferred. Non-limiting examples of compounds able to form an alkylmetallocene cation that can be used as component (B) are compounds of formula D^+E^- , wherein D^+ is a Brønsted acid, able to donate a proton and to react irreversibly with a substituent X of the metallocene of formula (I) and E^- is a compatible anion, which is able to stabilize the active catalytic species originating from the reaction of the two compounds, and which is sufficiently labile to be able to be removed by an olefinic monomer. Preferably, the anion E^- comprises of one or more boron atoms. More preferably, the anion E^- is an anion of the formula $BAr_4^{(-)}$, wherein the substituents Ar which can be identical or different are aryl radicals such as phenyl, pentafluorophenyl or bis(trifluoromethyl)phenyl. Tetrakis-pentafluorophenyl borate is particularly preferred examples of these compounds are described in WO 91/02012. Moreover, compounds of the formula BAr_3 can conveniently be used. Compounds of this type are described, for example, in WO 92/00333. Other examples of compounds able to form an alkylmetallocene cation are compounds of formula BAr_3P wherein P is a substituted or unsubstituted pyrrol radicals, and B is a boron atom. These compounds are described in WO01/62764. All these compounds containing boron atoms can be used in a molar ratio between boron and the metal of the metallocene

comprised between about 1:1 and about 10:1; preferably 1:1 and 2:1; more preferably about 1:1.

Non limiting examples of compounds of formula D^+E^- are:

Triethylammoniumtetra(phenyl)borate,
Tributylammoniumtetra(phenyl)borate,
Trimethylammoniumtetra(tolyl)borate,
Tributylammoniumtetra(tolyl)borate,
Tributylammoniumtetra(pentafluorophenyl)borate,
Tributylammoniumtetra(pentafluorophenyl)aluminate,
Tripropylammoniumtetra(dimethylphenyl)borate,
Tributylammoniumtetra(trifluoromethylphenyl)borate,
Tributylammoniumtetra(4-fluorophenyl)borate,
N,N-Dimethylaniliniumtetra(phenyl)borate,
N,N-Diethylaniliniumtetra(phenyl)borate,
N,N-Dimethylaniliniumtetrakis(pentafluorophenyl)borate,
N,N-Dimethylaniliniumtetrakis(pentafluorophenyl)aluminate,
Di(propyl)ammoniumtetrakis(pentafluorophenyl)borate,
Di(cyclohexyl)ammoniumtetrakis(pentafluorophenyl)borate,
Triphenylphosphoniumtetrakis(phenyl)borate,
Triethylphosphoniumtetrakis(phenyl)borate,
Diphenylphosphoniumtetrakis(phenyl)borate,
Tri(methylphenyl)phosphoniumtetrakis(phenyl)borate,
Tri(dimethylphenyl)phosphoniumtetrakis(phenyl)borate,
Triphenylcarbeniumtetrakis(pentafluorophenyl)borate,
Triphenylcarbeniumtetrakis(pentafluorophenyl)aluminate,
Triphenylcarbeniumtetrakis(phenyl)aluminate,
Ferroceniumtetrakis(pentafluorophenyl)borate,
Ferroceniumtetrakis(pentafluorophenyl)aluminate.
Triphenylcarbeniumtetrakis(pentafluorophenyl)borate,
N,N-Dimethylaniliniumtetrakis(pentafluorophenyl)borate.

Further compounds that can be used are those of formula $RM'-O-M'R$, R being an alkyl or aryl group, and M' is selected from an element of the Group 13 of the Periodic Table of the

Elements (new IUPAC version). Compounds of this type are described, for example, in the International patent application WO 99/40129.


Due to the particular stereoblock structure, the polymer of the present invention can also be used as component in a blend such as TPOs or other kind of heterophasic polymers blends. It can also form the isotactic polypropylene matrix produced in the first step of a multistep process for the production of reactor blends, such as the processes described in EP 720629 and EP 742801. Thus a further aspect of the present invention is a blend containing from 0.1% to 99.9% by weight of the porous polymer object of the present invention and from 0.1% to 99% by weight of one or more polymers, preferably one or more alpha-olefin polymers. Preferably the blend contains from 10% to 60% by weight, more preferably from 20% to 50% by weight of the porous polymer object of the present invention.

The polymers object of the present invention can be prepared by using catalyst components having particular morphological properties, obtained from adducts of magnesium chloride with alcohols containing generally 3 moles of alcohol per mole of MgCl_2 , which are prepared by emulsifying, in the molten state, the adduct in an inert hydrocarbon liquid immiscible with the melted adduct, then cooling the emulsion very rapidly in order to cause the solidification of the adduct in the form of spherical particles. The resultant particles are then subjected to partial dealcoholation using a heating cycle at temperature increasing from 50°C to 130°C. until the alcohol content is decreased from 3 to about 0.5-1.5 moles per mole of MgCl_2 . The adduct thus obtained is suspended cold in TiCl_4 , at a concentration of 40-50 g/l, and then brought to a temperature of 80°C to 135°C. where it is maintained for 1-2 hours. To this TiCl_4 is also added an electron-donor compound. The internal electron-donor compounds can be selected from ethers, esters, amines, ketones and the like. Non-limiting examples are alkyl esters, cycloalkyls and aryls of polycarboxylic acids, such as phthalic and maleic esters and ethers, such as those described in EP-A 45977, the disclosure of which is incorporated herein by reference. Preferably electron donor include mono or disubstituted phthalates wherein the substituents is a linear or branched C_{1-10} alkyl, C_{3-8} cycloalkyl, or aryl radical, such as for instance diisobutyl, di-n-butyl, and di-n-octyl phthalate. The excess TiCl_4 is then removed hot through filtration or sedimentation, and the treatment with TiCl_4 is repeated one or more times. The resulting solid is then washed with heptane or hexane and then dried. The catalyst component obtained is endowed with the following characteristics:


- surface area up to $100 \text{ m}^2/\text{g}$; preferably the surface area is comprised between 60 and $80 \text{ m}^2/\text{g}$;
- porosity (nitrogen) comprised between 0.25 and 0.35 cc/g ;
- porosity (Hg) comprised between 0.5 and 1 cc/g with the exclusion of macropores (pores having diameter $> 10000 \text{ \AA}$); and
- more than 50% of the pores have a radius greater than 100 angstrom.

The catalyst is obtained by mixing the solid catalyst component with an aluminum trialkyl compound, preferably aluminum triethyl or aluminum triisobutyl, and an electron donor compound (external donor).

The external donor preferably used has formula (I) or (II):



(I)



(II)

wherein

R^1 is a linear $\text{C}_4\text{-C}_{20}$ alkyl radical; preferably R^1 is a linear $\text{C}_4\text{-C}_{10}$ alkyl radical such as butyl, hexyl, octyl or decyl radical;

R^2 is a linear or branched, saturated or unsaturated $\text{C}_1\text{-C}_{20}$ alkyl, $\text{C}_3\text{-C}_{20}$ cycloalkyl, $\text{C}_6\text{-C}_{20}$ aryl, $\text{C}_7\text{-C}_{20}$ alkylaryl or $\text{C}_7\text{-C}_{20}$ arylalkyl radical; preferably R^2 is a linear $\text{C}_1\text{-C}_{20}$ alkyl radical such as methyl, ethyl, propyl, butyl, hexyl, octyl or decyl radical;

R^3 is a linear or branched, saturated or unsaturated $\text{C}_1\text{-C}_{20}$ alkyl, $\text{C}_3\text{-C}_{20}$ cycloalkyl, $\text{C}_6\text{-C}_{20}$ aryl, $\text{C}_7\text{-C}_{20}$ alkylaryl or $\text{C}_7\text{-C}_{20}$ arylalkyl radical optionally containing heteroatoms of group 13-16 of the periodic table; preferably R^3 is a linear $\text{C}_1\text{-C}_4$ alkyl or $\text{C}_1\text{-C}_{20}$ alkoxy radical. The Al/Ti ratio is generally from 10 to 800 and the molar silane/Al ratio is typically from 1/5 to 1/50. The (co)polymerization of propylene is done according to known techniques operating in liquid monomer or gas phase. The polymerization temperature is generally from 0°C to 100°C , preferably from 30°C to 90°C , more preferably from 70°C to 90°C . The catalysts can be precontacted with small quantities of olefin (prepolymerization), maintaining the catalyst in suspension in a hydrocarbon solvent, polymerizing at a temperature between room temperature and 60°C for a time sufficient to produce quantities of polymer from 0.5 to 3 times the weight of the catalyst.

Prepolymerization in a monomer liquid can also be done, producing in this case quantities of polymer up to 1000 times the weight of the catalyst. The polymer of the present invention can be used as inert support for a catalyst component in a process for the polymerization of olefins. The polymer of the present invention can be used, for example, by adding to a suspension in propane of the porous polymer a solution or a suspension of the catalyst system, under stirring. Then the propane is removed, for example, by flashing the solution thus obtaining the supported catalyst.

EXAMPLES

GENERAL PROCEDURES

The data shown in the Examples relative to the properties of the porous polymers of the present invention were determined according to the methods indicated below.

MIL flow index: ASTM-D 1238

Intrinsic viscosity (I.V.): measured in tetrahydronaphtalene (THN) at 135°C.

Fraction soluble in xylene:

2 g of polymer were dissolved in 250 ml of xylene at 135°C under stirring. After 20 minutes the solution was left to cool, still under stirring, up to 25°C. After 30 minutes the precipitated material was filtered through filter paper, the solution was evaporated in nitrogen current and the residual was dried under vacuum at 80°C until it reached constant weight. Thus, the percentage of polymer soluble in xylene at room temperature was calculated.

Porosity (mercury):

determined by immersing a known quantity of the sample in a known quantity of mercury inside a dilatometer and gradually hydraulically increasing the pressure of the mercury. The pressure of introduction of the mercury in the pores is in function of the diameter of the same. The measurement was carried out using a porosimeter "Porosimeter 2000 Series" (C. Erba). The total porosity was calculated from the volume decrease of the mercury and the values of the pressure applied. The porosity expressed as percentage of voids is determined by absorption of mercury under pressure. The volume of mercury absorbed corresponds to the volume of the pores. For this determination, a calibrated dilatometer (diameter 3 mm) CD3 (Carlo Erba) connected to a reservoir of mercury and to a high-vacuum pump (1.10^{-2} mbar) is used. A weighed amount of sample (about 0,5 g) is placed in the dilatometer. The apparatus is then placed under high vacuum ($<0,1$ mm Hg) and is maintained in these conditions for 10 minutes. The dilatometer is then connected to the mercury reservoir and the mercury is allowed to flow slowly into it until it reaches the level marked on the dilatometer at a height

of 10 cm. The valve that connects the dilatometer to the vacuum pump is closed and the apparatus is pressurised with nitrogen (2,5 Kg/cm²). Under the effect of the pressure, the mercury penetrates into the pores and the level goes down according to the porosity of the material. Once the level at which the mercury has stabilised has been measured on the dilatometer, the volume of the pores is calculated from the equation $V = R^2\pi\Delta H$, where R is the radius of the dilatometer and ΔH is the difference in cm between the initial and the final levels of the mercury in the dilatometer. By weighting the dilatometer, dilatometer+mercury, dilatometer+mercury+sample, the value of the apparent volume V_1 of the sample prior to penetration of the pores can be calculated. The volume of the sample is given by:

$$V_1 = [P_1 - (P_2 - P)]/D$$

P is the weight of the sample in grams, P_1 is the weight of the dilatometer+mercury in grams, P_2 is the weight of the dilatometer+mercury+sample in grams, D is the density of mercury (at 25°C = 13,546 g/cm). The percentage porosity is given by the relation:

$$X = (100V)/V_1.$$

Bulk density: DIN-53194.

Morphology: ASTM-D-1921-63.

Flexural modulus: ASTM D-5023.

Compression. Set: ASTM D395 22hr/70°C.

Hardness Shore A: ASTM D2240.

Modulus 100, psi: ASTM D412.

Tensile strength: ASTM D412.

Elongation: ASTM D412.

Tension set: ASTM D412.

Temperature Rising Elution Fractionation (TREF) technique:

carried out as described in EP 658 577.

Example 1 (comparative)

The solid titanium catalyst component was prepared according to example 2 of EP-A-395 083.

Using 0,011 g of this solid, a propylene polymerization was carried out in a 4 l autoclave equipped with magnetically driven stirrer and a thermostatic system, previously fluxed with nitrogen at 70°C for one hour and then with propylene. Into the reactor at room temperature, without stirring but under propylene stream, a catalyst system consisting of a suspension of

the solid component in 15 ml of hexane, 1.14 g of triethylaluminium, and 114 mg of dicyclopentyl dimethoxysilane (donor D) is introduced, this system is prepared just prior to its use in the polymerization test. The autoclave is then closed and 3 l of hydrogen are introduced. Under stirring, 1.3 Kg of propylene was charged and the temperature was brought to 70 °C in 5 minutes, maintaining the value constant for two hours. At the end of the test, the stirring was stopped and the unreacted propylene was vented off. After cooling the autoclave to room temperature, the polymer is recovered and then dried at 70°C under a nitrogen stream in an oven for 3 hours. 418 g of spherical polymer. The characteristics of the polymer are reported in table 1.

Example 2 (comparative)

The solid titanium catalyst component was prepared according to example 2 of EP-A-395 083. A polymerization reactor was heated to 70°C, purged with a slow argon flow for 1 hour, its pressure was then raised to 100 psi-g with argon at 70°C and then the reactor was vented. This procedure was repeated 4 more times. The reactor was then cooled to 30°C. Separately, into an argon purged addition funnel, the following were introduced in the order they are listed; 75 mL of hexane, 4.47 mL of 1.5 M solution of triethylaluminum (TEAL) (0.764 g 6.70 mmol) in hexane, approximately 0.340 mmol of dicyclopentyl dimethoxy silane (donor D) (TEAL/D about 20:1) and allowed to stand for 5 minutes. Of this mixture, 35 mL was added to a flask. Then 0.0129 of the catalyst component previously prepared was added to the flask and mixed by swirling for a period of 5 minutes. The catalytic complex so obtained was introduced, under an argon purge, into the polymerization reactor at room temperature. The remaining hexane/TEAL/silane solution was then drained from the additional funnel to the flask, the flask was swirled and drained into the reactor and the injection valve was closed. The polymerization reactor was slowly charged with 2.2. L of liquid propylene and H₂ while stirring. Then the reactor was heated to 70°C maintaining the temperature and pressure constant for about 2 hours. After about two hours agitation was stopped and the remaining propylene was slowly vented. The reactor was heated to 80°C, purged with argon for 10 minutes and then cooled to room temperature and opened. The polymer was removed and dried in a vacuum oven at 80°C for 1 hour.

The characteristics of the polymer are reported in table 1.

Example 3

The procedure for the preparation of the polymer of example 2 was followed excepting that

butylmethyldimethoxy silane (BuMeMS) was used as external donor instead of dicyclopentyl dimethoxy silane.

The characteristics of the polymer are reported in table 1.

Example 4

The procedure for the preparation of the polymer of example 2 was followed excepting that Octilmethyldimethoxy silane (OctMeMS) was used as external donor instead of dicyclopentyl dimethoxy silane.

The characteristics of the polymer are reported in table 1.

Polymerization Examples 5-8

The amount of polypropylene as described in table 2 were charged into a reactor of 4 L of capacity, under propane atmosphere (pressure 1 bar), at room temperature, without any stirring. 250 g of propane were added at room temperature under stirring (a pressure of about 10 bar was achieved). 4,4 g of 5-ethylidene-2-norbornene (ENB) were added thereafter, by a little nitrogen overpressure, under stirring at room temperature for 10 minutes and then propane was flashed under stirring. 250 g of propane were then added at room temperature under stirring and the temperature was brought to 40°C. In the meantime, rac-ethylenbis(tetrahydroindenyl)ZrCl₂ (rac EBTHIZrCl₂), methyl alumoxane (MAO) and Al(isooctyl)₃ (TIOA) were dissolved in 10 ml of toluene at room temperature for ten minutes (amounts reported in table 2). The catalyst solution was then injected into the reactor by a little nitrogen overpressure. The suspension in the reactor was stirred at 40°C for 10 minutes. Then the reactor was vented. Propane was added thereto, to achieve a pressure of 6 bar-g at 30 °C. A 50/50 ethylene/propylene mixture was fed to the reactor, in 5 minutes, bringing the pressure to 20 bar-g and the temperature to 60°C. During the whole course of the polymerisation the temperature was kept constant at 60° and the pressure too was maintained constant at 20 bar-g by continuously feeding an ethylene/propylene mixture in a 60/40 wt/wt ratio. During the polymerisation 16 ml of a pentane solution containing an amount of ENB reported in table 1 was continuously added dropwise.

The polymerisation was stopped by quickly degassing the monomers. The polymer was plunged in 800 ml of methanol and filtered.

The filtered polymer was plunged again in 800 ml of methanol containing Irganox 1020, added to be about 200 ppm on the polymer.

Methanol was then evaporated with a nitrogen stream under reduced pressure at 60°C.

Polymerization data and characterization data of the obtained polymers are reported in table 2.

Table 1

Ex	H ₂ Mol %	I.V. (dl/g)	XSRT %	Bulk density g/cc	flexural modulus Mpa	melting enthalpy J/g	melting point g	Pore volume cc/g	Average radius μm	TREF 25-97°C %
1*	n.a.	1.49	3.50	0.36	n.a.	n.a.	n.a.	0.54	8.7	n.a.
2*	0.15	2.12	3.35	0.29	1500	89	164.8	0.67	15	8.0
3	0.10	1.53	9.24	0.31	920	87	159.9	0.58	14	41.0
4	0.10	1.48	n.a.	0.30	830	106	159.8	0.66	15	40.3

n.a. = not available * comparative

Table 2

Ex	PP Ex (g)	EBTHI mg	MAO mmol	TiAO mmol	Al/Zr	Diene g	Time min	Activity Kg/gcat	ENB % wt	ET % wt	Split rubber % wt	I.V. tot (dl/g)
5*	1 (175)	14	1.09	5.47	200	7.9	120	23.7	2.0	65	62	2.8
6*	2 (150)	14	1.09	5.47	200	9.7	55	22.5	2.5	61	68	2.0
7	3 (150)	8	0.63	3.13	200	6.6	160	30.6	2.0	64	62	2.1
8	4 (150)	8	0.63	3.13	200	8.36	110	37.5	2.3	61	68	2.0

* comparative

CLAIMS

1. A porous polymer of propylene, optionally containing up to 15% by weight of an alpha-olefin of formula $\text{CH}_2=\text{CHR}$ wherein R is a hydrogen atom or a $\text{C}_2\text{-C}_{10}$ alkyl radical, said porous propylene polymer having the following characteristics:
 - a) in the Temperature Rising Elution Temperature analysis (TREF) a fraction eluted at a temperature range of from 25°C to 97° higher than 20% of the total polymer eluted; and
 - b) a pore volume (determined by mercury absorption) greater than 0.45 cc/g.
2. The polymer according to claim 1 wherein the flexural modulus (METHOD ASTM D-5023) lower than 1200 Mpa.
3. The polymer according to claims 1 or 2 wherein the porous polymer has a melting enthalpy lower than 90 J/g.
4. The polymer according to anyone of claims 1-3 wherein: in the Temperature Rising Elution Temperature analysis (TREF) the fraction eluted at a temperature range from 25°C to 97° is higher than 30%; of the total polymer eluted.
5. The polymer according to anyone of claims 2-4 wherein the flexural modulus (METHOD ASTM D-5023) is lower than 1000 Mpa.
6. The polymer according to anyone of claims 3-5 wherein the pore volume (determined by mercury absorption) is greater than 0.50 cc/g.
7. An heterogeneous catalyst system comprising:
 - A) a porous polymer of propylene containing up to 15% by weight of an alpha-olefins of formula $\text{CH}_2=\text{CHR}$ wherein R is a hydrogen atom or a $\text{C}_2\text{-C}_{10}$ alkyl radical having the following characteristics:
 - a) in the Temperature Rising Elution Temperature analysis (TREF) a fraction eluted at a temperature range from 25°C to 97° higher than 20% of the total polymer eluted; and
 - b) a pore volume (determined by mercury absorption) greater than 0.45 cc/g;
 - B) a metallocene compound; and
 - C) an alumoxane or a compound able to form an alkylmetallocene cation.
8. A blend containing from 0.1% to 99.9% by weight of the porous polymer as claimed in anyone of claims 1-6, and from 99.9% to 0.1% by weight of one or more polymers.

9. The blend according to claim 8 wherein the one or more polymers are one or more alpha-olefin polymers.

INTERNATIONAL SEARCH REPORT

In International Application No

PCT/EP 02/13471

A. CLASSIFICATION OF SUBJECT MATTER
 IPC 7 C08F10/06 C08F4/02

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C08F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 96 02583 A (MONTELL TECHNOLOGY COMPANY BV) 1 February 1996 (1996-02-01) cited in the application page 5, line 15 -page 7, line 12 page 10, line 1 - line 8 page 19, line 11 - line 18; claims; examples	1-9
X	& EP 0 720 629 B 6 May 1999 (1999-05-06) ----	
X	WO 96 11218 A (MONTELL TECHNOLOGY COMPANY BV) 18 April 1996 (1996-04-18) cited in the application page 4, line 12 -page 6, line 24 page 8, line 11 - line 24 page 11, line 12 - line 18 claims; examples	1-9
X	& EP 0 742 801 B 11 April 2001 (2001-04-11) ----- -/--	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

A document defining the general state of the art which is not considered to be of particular relevance

E earlier document but published on or after the international filing date

L document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

O document referring to an oral disclosure, use, exhibition or other means

P document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

* & * document member of the same patent family

Date of the actual completion of the international search

23 April 2003

Date of mailing of the international search report

06/05/2003

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
 NL - 2280 HV Rijswijk
 Tel (+31-70) 340-2040, Tx. 31 651 epo nl,
 Fax: (+31-70) 340-3016

Authorized officer

Kaumann, E

INTERNATIONAL SEARCH REPORT

International Application No
PCT/EP 02/13471

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 00 00517 A (GALIMBERTI MAURIZIO ;BARUZZI GIOVANNI (IT); MONTELL TECHNOLOGY COM) 6 January 2000 (2000-01-06) page 2, line 23 -page 4, line 4; claims; example 3 ---	1-6
A	EP 0 395 083 A (HIMONT INC) 31 October 1990 (1990-10-31) cited in the application page 4, line 30 -page 5, line 6; claims; examples ---	1-6
X	US 5 556 893 A (FRANCOIS PHILIPPE ET AL) 17 September 1996 (1996-09-17) column 1, line 63 -column 2, line 15; claims ---	1-6
P,X	WO 02 051887 A (BASELL POLIOLEFINE ITALIA S P ;FERRARO ANGELO (IT); FUSCO OFELIA ()) 4 July 2002 (2002-07-04) claims 1,13; examples 3-6; table 1 -----	1-9

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 02/13471

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
WO 9602583	A	01-02-1996	IT 1273660 B	09-07-1997
			AT 179724 T	15-05-1999
			AU 693239 B2	25-06-1998
			AU 3113295 A	16-02-1996
			BG 63015 B1	31-01-2001
			BG 100515 A	31-01-1997
			BR 9506342 A	05-08-1997
			CN 1134712 A ,B	30-10-1996
			CZ 9601135 A3	16-10-1996
			DE 69509488 D1	10-06-1999
			DE 69509488 T2	04-11-1999
			DK 720629 T3	01-11-1999
			WO 9602583 A1	01-02-1996
			EP 0720629 A1	10-07-1996
			ES 2132695 T3	16-08-1999
			FI 961268 A	02-05-1996
			HU 74779 A2	28-02-1997
			IL 114638 A	31-12-1999
			JP 9503250 T	31-03-1997
			NO 961108 A	10-05-1996
			PL 313587 A1	08-07-1996
			RU 2176252 C2	27-11-2001
			SK 49396 A3	05-03-1997
			TR 960075 A2	21-06-1996
			TW 424099 B	01-03-2001
			US 5589549 A	31-12-1996
			ZA 9505987 A	18-06-1996
WO 9611218	A	18-04-1996	IT 1270125 B	28-04-1997
			AT 200499 T	15-04-2001
			AU 694276 B2	16-07-1998
			AU 3803395 A	02-05-1996
			BG 100674 A	31-03-1997
			BR 9506402 A	09-09-1997
			CA 2178077 A1	18-04-1996
			CN 1139934 A ,B	08-01-1997
			CZ 9601994 A3	11-12-1996
			DE 69520662 D1	17-05-2001
			DE 69520662 T2	18-10-2001
			DK 742801 T3	21-05-2001
			WO 9611218 A1	18-04-1996
			EP 0742801 A1	20-11-1996
			ES 2156948 T3	01-08-2001
			FI 962329 A	04-06-1996
			GR 3035745 T3	31-07-2001
			HU 75175 A2	28-04-1997
			IL 115515 A	26-07-2000
			JP 9506391 T	24-06-1997
			NO 962298 A	04-06-1996
			PL 314853 A1	30-09-1996
			PT 742801 T	30-08-2001
			RU 2171265 C2	27-07-2001
			SK 87296 A3	09-04-1997
			TR 960285 A2	21-06-1996
			US 5648422 A	15-07-1997
			US 6028140 A	22-02-2000
			ZA 9508316 A	26-04-1996

INTERNATIONAL SEARCH REPORT

Int'l Application No

PCI/EP 02/13471

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
WO 0000517	A	06-01-2000	CA 2301618 A1	06-01-2000
			CN 1275133 T	29-11-2000
			WO 0000517 A1	06-01-2000
			EP 1015500 A1	05-07-2000
			JP 2002519447 T	02-07-2002
EP 0395083	A	31-10-1990	IT 1230134 B	14-10-1991
			AT 160150 T	15-11-1997
			AU 636142 B2	22-04-1993
			AU 5456990 A	01-11-1990
			BR 9001991 A	13-08-1991
			CA 2015685 A1	28-10-1990
			CN 1047302 A ,B	28-11-1990
			CZ 9900469 A3	17-01-2001
			DD 298935 A5	19-03-1992
			DE 69031693 D1	18-12-1997
			DE 69031693 T2	14-05-1998
			EP 1251141 A2	23-10-2002
			EP 0395083 A2	31-10-1990
			EP 0789037 A2	13-08-1997
			ES 2110399 T3	16-02-1998
			FI 103124 B1	30-04-1999
			FI 970960 A	06-03-1997
			HK 1004605 A1	27-11-1998
			HU 62609 A2	28-05-1993
			IL 94154 A	25-01-1994
			JP 3016816 B2	06-03-2000
			JP 3062805 A	18-03-1991
			JP 3193360 B2	30-07-2001
			JP 2000080121 A	21-03-2000
			KR 177803 B1	15-05-1999
			MX 20477 A	01-12-1993
			NO 901912 A ,B,	29-10-1990
			PL 284968 A1	13-01-1992
			PL 165373 B1	30-12-1994
			PL 165028 B1	30-11-1994
			PT 93923 A ,B	20-11-1990
			SK 74798 A3	14-02-2000
			SK 210990 A3	11-01-1999
			RU 2045537 C1	10-10-1995
			US 5221651 A	22-06-1993
			YU 82990 A1	31-10-1991
			ZA 9003063 A	30-01-1991
US 5556893	A	17-09-1996	BE 1007040 A3	28-02-1995
			AT 178617 T	15-04-1999
			AU 681125 B2	21-08-1997
			AU 6322594 A	01-12-1994
			BR 9402065 A	20-12-1994
			CA 2124176 A1	26-11-1994
			CN 1100343 A ,B	22-03-1995
			CZ 9401270 A3	15-12-1994
			DE 69417621 D1	12-05-1999
			DE 69417621 T2	21-10-1999
			DK 627447 T3	25-10-1999
			EP 0627447 A1	07-12-1994
			ES 2132322 T3	16-08-1999
			FI 942427 A	26-11-1994

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 02/13471

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5556893	A	HK 1013658 A1	05-05-2000
		HU 69050 A2	28-08-1995
		JP 6329715 A	29-11-1994
		NO 941923 A	28-11-1994
		RO 112875 B1	30-01-1998
		RU 2131439 C1	10-06-1999
		SG 54161 A1	19-12-2001
		SK 60594 A3	08-02-1995
		US 6221802 B1	24-04-2001
		US 5756613 A	26-05-1998
		US 2001014727 A1	16-08-2001
		ZA 9403656 A	26-01-1995
WO 02051887	A	04-07-2002	WO 02051887 A2
			04-07-2002